



IB BLEED BLOCK is a high performance, plasticizer free, single component, water-based, acrylic elastomeric base coating that is designed as a base coat over a variety of substrates to help reduce asphaltic bleed through and discoloration of the finish coat.

PACKAGING

5 gallon Pail, 55 Gallon Drum, & 275 Gallon Tote

FEATURES AND BENEFITS

- Plasticizer free
- 55% solids by volume
- Excellent adhesion to a variety of substrates
- Special bleed resistant formulation helps retard asphaltic bleed through and discoloration of finish coats
- Unique formulation allows breathable film while providing a watertight membrane and permitting trapped moisture to escape
- Low VOC, less than 50 grams/liter
- Available in gray

PRODUCT USE

IB Bleed Block is used as a base coat over granule surfaced asphalts, and modified bitumen to help reduce asphaltic bleed through and discoloration of the finish coat and over single ply substrates to help reduce plasticizer migration and discoloration of the finish coat.

ORDERING INFORMATION

IB Bleed Block

| Item Code | Description | Size | Class |
|-----------|---------------------|---------|-------|
| 9-BBG | IB Bleed Block Gray | 5-gal | 55 |
| 9-BBG55 | IB Bleed Block Gray | 55-gal | 55 |
| 9-BBG275 | IB Bleed Block Gray | 275-gal | 55 |

COVERAGE RATE (APPROXIMATE)

Approximate coverage rate is 1.0 – 1.5 gallons per 100 square feet (16-24 wet mils) per pass depending on substrate type and roughness.

Yield (1 gal/100 sq. ft.) = 16 wet mils/8.8 dry mils.

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

Physical Properties

| Property | Test Method | Typical Value |
|---|-------------|-------------------------------------|
| % Solids by Volume | D2697 | 55% ± 3% |
| % Solids by Weight | D1644 | 68% ± 3% |
| Viscosity | D562 | 100 KU |
| Elongation | D2370 | 315% (initial) 200% (aged) |
| Tensile Strength | D2370 | 310 psi (initial) 400 psi (aged) |
| Low Temperature Flexibility | D522 | Pass @ -15°F (-26.1°C) |
| Permeance | D1653 | Perms 9 ± 1 |
| Weight per Gallon | - | 11.9 lbs./gal |
| VOC Content | EPA M24 | <50 g/L |
| Fungi Resistance | - | Zero Rating |
| Water Swell | - | 10% |
| Dry Time @ 75°F (25°C) | - | 90 minutes @ 50% humidity |
| Recoat Window | - | 6-24 hours to recoat |
| Cure Time | - | 30 days |
| Shelf Life: (unopened container stored at temperatures between 60°F and 95°F. | - | 12 months from date of manufacture. |

TEMPERATURE PRECAUTIONS

Do not apply this product below 40°F (4.4°C) or in weather conditions where the temperature will drop below 40°F (4.4°C) during the curing cycle. Upper temperature restriction (both air and substrate) for application of IB Coating products is 120°F (49°C). If the substrate temperature exceeds 120°F (49°C), IB Coating products should be applied during cooler periods of the day. No coating should be applied unless surface temperature is 40°F minimum and 120°F maximum.

RELATIVE HUMIDITY PRECAUTIONS

Acrylic products are moisture sensitive. Do not apply this product when it is raining or if the threat of rain exists. Do not apply when the dew point is less than 5°F below the ambient temperature. Do not apply in conditions when the relative humidity exceeds 90%.

STORAGE

Always store in cool and dry location. For best results, keep product stored above 50°F (10°C) or below 90°F (32°C). Do not store in direct sunlight or in temperatures. Keep from freezing. Allow material to set at room temperature for 24 hours prior to use.

APPLICATION GUIDELINES

Application Equipment

Airless Sprayer:

- **Output:** Minimum 30:1 fluid to air ratio / 2.5 – 3.0 gal per minute
- **Pressure:** 3,000 to 4,000 psi
- **Filter Screen:** 30 mesh or larger
- **Spray Gun:** Contractor rated for pressure, equipped with a ball-bearing swivel for ease of handling
- **Hoses:** 3/8" min ID up to 75 ft., 1/2" min ID up to 200 ft., and 3/4" min ID over 200 ft. Use largest diameter at pump. Hoses rated to 2X maximum pump pressure. Hose lining should be compatible with coating and required cleaning materials.
- **Gun Hose:** 3/8" ID x 6 feet high pressure rated with adequate WPSI.
- **Extension:** 12" gun extension is recommended
- **Orifice Tip:** .027" to .039" diameter, wide angled fan angle of 40 to 50 degrees is recommended. A reversible self-cleaning type nozzle is also recommended. Exact orifice size will vary with temperature of the material and ambient temperatures.
- **Brush:** No reduction necessary. Use synthetic filament brushes. Do not over-brush as material may start to pull.
- **Roller:** No reduction necessary. Use 1-1/4" nap synthetic rollers. Keep a wet edge to avoid pulling. Avoid rapid rolling which can cause bubbling.
- **Spraying:** When spraying material should be at least 75°F (25°C). Before applying additional coat, the previous coat must be completely dry and cured.

Mixing

No thinning or reduction is necessary. Product may separate after shipping and storage, though it may still appear mixed. When mixing is necessary, use a ¾ horsepower or larger electric or air operated mixer with a blade capable of uniformly mixing container. Use a 3" minimum diameter mixing blade for 5-gal pails and a minimum 6" minimum diameter blade for drums. **Never mix by hand.**

Surface Preparation

The substrate must be free of areas of ponding water, ice, snow, rain or dew, dirt, dust, grease, oil, foreign contaminants or other debris that would inhibit adhesion of coating. If such conditions exist, the roof surfaces should be properly prepared and cleaned using the specified IB cleaning solution in order to receive the new coating system.

Mildew must be removed by power washing and scrubbing with a bleach solution of 1 part bleach and 2 parts water. Repeat if necessary. Rinse thoroughly and allow to dry.

Most substrates require a compatible primer to be applied prior to the application of the coating. Contact IBRS Technical Department at 800-426-1626 for recommendations regarding specific applications.

Application

Aged Mineral Cap & Granulated Modified Bitumen: To properly prepared substrate apply a base coat of IB Bleed Block at the rate of 1.0–1.5 gallons (3.78–5.67 L) per 100 square feet (16–24 wet mils). Once completely dry, the IB Bleed Block may be coated with a finish coat of IB Acrylic or Silicone Coating.

Aged Thermoplastic (Hypalon/TPO/PVC): To properly prepared substrate apply a base coat of IB Bleed Block at the rate of 0.5 - 1.0 gallons (1.89–3.78 L) per 100 square feet (8–16 wet mils). Once completely dry, the IB Bleed Block may be coated with a finish coat of IB Acrylic Coating.

Adhesion Test: Adhesion of the IB Bleed Block should always be checked. Apply 6" – 12" square of the coating and embed a piece of IB Fabric into the coating, leaving a minimum 2" tail of the fabric exposed. Allow 2-3 days for the coating to cure and perform a 90° pull test of the fabric tail to test adhesion of the coating to the substrate.

Limitations

- Refer to Substrate Preparation guidelines for proper preparation, cleaning and primer roof with any applicable bond enhancing primer before commencing with application of IB Acrylic Coatings.
- This product cures by water evaporation only. Do not attempt to apply product when weather conditions are not conducive to drying. Refer to temperature and relative humidity precautions.
- Application of materials with power spray equipment will require some masking and erection of wind screens to prevent over spray occurrences and damage to surrounding structures, surfaces, vehicles, property or persons.

Clean Up

Clean up spills and splatters immediately with water. Flush all hoses, equipment, and tools with water followed by propylene glycol to prevent unit from rusting.

Disposal

Empty containers must be disposed of in an approved landfill in accordance with local, state, and federal regulations.

Caution

Avoid prolonged and repeated contact with skin. Do not take internally. Avoid eye contact as this material has adhesive properties. Refer to product Safety Data Sheet (SDS) for additional information pertaining to this product and prior to use or handling.

Disclaimer

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product only.

LIMITED PRODUCT WARRANTY

IB ROOF SYSTEMS, INC. ("IB") WARRANTS THE IB LABELED COATING PRODUCTS ("IB PRODUCT") SHALL BE FREE FROM ANY DEFECT IN MANUFACTURING FOR A PERIOD OF ONE (1) YEAR FROM DATE OF PURCHASE FROM IB. UPON IB'S RECEIPT OF WRITTEN NOTICE WITHIN THE WARRANTY PERIOD, IB WILL SHIP REPLACEMENT IB PRODUCT TO THE JOBSITE OR (AT IB'S SOLE DISCRETION) REFUND THE ORIGINAL PURCHASE PRICE, FOR ANY IB PRODUCT PROVED TO BE DEFECTIVE IN ITS MANUFACTURE. MISUSE, OR INSTALLATION OR STORAGE OR HANDLING OF IB PRODUCT IN ANY MANNER CONTRARY TO IB SPECIFICATIONS, INSTRUCTIONS OR RECOMMENDATIONS SHALL VOID THE COVERAGE PROVIDED HEREIN. THIS LIMITED PRODUCT WARRANTY IS ALSO VOID IF THE IB PRODUCT IS PAINTED, PATCHED, ALTERED OR COVERED IN ANY WAY WITH ANY OTHER PRODUCT OR MATERIAL. THIS LIMITED WARRANTY IS EXCLUSIVE AND REPLACES ALL OTHER WARRANTIES, PROMISES, REPRESENTATIONS AND GUARANTEES, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THIS LIMITED PRODUCT WARRANTY IS THE EXCLUSIVE WARRANTY FROM IB AND REPRESENTS THE SOLE REMEDY AVAILABLE TO ANY OWNER OR USER OF IB THE PRODUCT HEREIN. IB MAKES NO OTHER REPRESENTATIONS, PROMISES, GUARANTEES, OR WARRANTIES OF ANY KIND OTHER THAN THAT STATED HEREIN. NO REPRESENTATIVE, EMPLOYEE, OR AGENT OF IB, OR ANY OTHER PERSON, HAS AUTHORITY TO ALTER THE TERMS OF THIS LIMITED PRODUCT WARRANTY. IB WILL NOT BE LIABLE IN ANY EVENT FOR ANY DIRECT, CONSEQUENTIAL, PUNITIVE, SPECIAL, INCIDENTAL, OR OTHER SIMILAR DAMAGES OF ANY KIND, INCLUDING BUT NOT LIMITED TO PHYSICAL OR ECONOMIC DAMAGE TO THE ANY ELEMENTS OF ANY BUILDING (INTERIOR OR EXTERIOR COMPONENTS), FOR MOLD OR OTHER BIOLOGICAL GROWTH, ODOR, DISCOLORATION, CHEMICAL REACTION OR LOSS OF USE, REGARDLESS OF WHETHER ANY SUCH DAMAGE CLAIM AGAINST IB IS BASED UPON BREACH OF THIS WARRANTY, NEGLIGENCE, STRICT LIABILITY IN TORT, OR FOR ANY OTHER LEGAL THEORY OR CAUSE. THIS LIMITED PRODUCT WARRANTY SHALL BE GOVERNED BY THE LAWS OF THE STATE OF TEXAS, WITHOUT REGARD TO PRINCIPLES OF CONFLICTS OF LAWS, AND ALL PARTIES TO DISPUTES HEREUNDER AGREE AND CONSENT TO EXCLUSIVE JURISDICTION OF AND VENUE IN THE COURTS OF DALLAS COUNTY, TEXAS. SOME JURISDICTIONS DO NOT ALLOW LIMITATIONS ON OR THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE ABOVE LIMITATIONS OR EXCLUSIONS MAY NOT APPLY TO YOU. THIS LIMITED PRODUCT WARRANTY GIVES YOU SPECIFIC LEGAL RIGHTS, AND YOU MAY ALSO HAVE OTHER RIGHTS WHICH VARY FROM JURISDICTION TO JURISDICTION.